

**TECHNICAL DATA SHEET**

BOOP PACKING TAPE /BOPP	Hystik SC-2017-8
Composition	BOPP Film: 0.025 mm, Acrylic adhesive 0.020 mm

Test Item	Dimension & Tolerances	Result	Test Method
Batch No/Rool No.		No. 264588(#A18)	ASTM D-1000
Overall Thickness (mm)	0.045	0.045	ASTM D-1000
Base Film Thickness (mm)	0.025	0.025	ASTM D-1000
Adhesive Thickness (mm)	0.020	0.020	PSTC-6
Ball Tack (cm)	<7	2.8	ASTM D-1000
Adhesion to Steel	5.8N	6.41N	PSTC-7
Holding Power (min/15mm*25mm)	>16	20	ASTM D882
Tensile Strength N/10mm		30.28N	ASTM D882
Elongation at Break (%)		114.67%	
Adhesive Peel Off	NO	NO	
Overall Comment	qualified		

Remark: Laboratory Temperature: 25°C	Laboratory Humidity: 38%
Remark: Outdoor Temperature: 23°C	Outdoor Humidity: 55%